

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b> <b>A61K 9/50</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/44912</b> <b>(43) International Publication Date:</b> 15 October 1998 (15.10.98)
<b>(21) International Application Number:</b> PCT/US98/04462 <b>(22) International Filing Date:</b> 6 March 1998 (06.03.98)  <b>(30) Priority Data:</b> 08/834,971      7 April 1997 (07.04.97)      US  <b>(71) Applicant:</b> MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).  <b>(72) Inventors:</b> SENGUPTA, Ashok; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). NIELSEN, Kent, E.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). BARIN-SHTEYN, Galina; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). LI, Kai; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). BANOVELTZ, John; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).  <b>(74) Agents:</b> BJORKMAN, Dale, A. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> ADHERENT MICROCAPSULES CONTAINING BIOLOGICALLY ACTIVE INGREDIENTS  <b>(57) Abstract</b>  An aqueous suspension of microcapsules containing a biologically active material comprises an adhesive material in an amount effective to enable said microcapsules to adhere to an intended substrate.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

ADHERENT MICROCAPSULES CONTAINING BIOLOGICALLY ACTIVE INGREDIENTS

---

FIELD OF THE INVENTION

The present invention relates to suspensions of adherent capsules containing  
5 biologically active ingredients.

BACKGROUND OF THE INVENTION

It is known to encapsulate various materials, often by interfacial  
polycondensation. For instance, United States Patent No. 3,577,515 speaks of  
10 capsules containing dyes, inks, chemical reagents, pharmaceuticals, flavoring  
material, pesticides, herbicides, peroxides and indeed anything which can be  
dissolved, suspended or otherwise constituted in or as a liquid enclosed by the  
capsule. United Kingdom Patent No. 1,371,179 discloses the preparation of  
polyurea capsules for containing dyes, inks, chemical reagents, pharmaceuticals,  
15 flavoring materials, fungicides, bactericides and pesticides such as herbicides and  
insecticides. United States Patents Nos. 4,046,741; 4,140,516; 4,417,916;  
4,563,212 and European Patent No. 611,253 are concerned with encapsulation of  
various materials. Canadian Patent No. 1,044,134 is concerned with encapsulation  
of insecticides, particularly pyrethroids. Canadian Patent No. 1,179,682 is  
20 concerned with encapsulation of pheromones. A pending United States Patent  
Application (attorney docket number 53319USA6A), filed on even date with this  
application, is also concerned with encapsulating various materials, including  
biologically active materials such as pheromones.

The above-mentioned patents make use of various forms of interfacial  
25 polycondensation, particularly the formation of capsules having polyurea and/or  
polyurethane/polyurea shell walls. The capsules made by the various processes are  
said to range in diameter from about 1 micron to about 2 mm, but most fall towards  
the lower end of this range, i.e., from about 250 microns, or even 100 microns,  
down to about 1 micron.

30

### SUMMARY OF THE INVENTION

An aqueous suspension of microcapsules containing a biologically active material, which suspension further comprises an adhesive material in an amount effective to enable said microcapsules to adhere to an intended substrate.

### DESCRIPTION OF THE PREFERRED EMBODIMENTS

For purposes of the present invention, the term "biologically active" means materials that affect the life processes of organisms. Materials that are biologically active include herbicides, pesticides, pharmaceuticals, and semiochemicals, including naturally and artificially produced pheromones.

Microcapsules containing such biologically active ingredients and additionally containing an adhesive material advantageously may be applied by spraying. This is particularly advantageous in the fields of forestry, agriculture and horticulture, where aerial spraying is preferred as a means of application. The sprayed capsules are applied to foliage, to which continued contact is desired. For instance, insecticides and pheromones should remain on the foliage if they are to display maximum effect. In the absence of the adhesive material described herein, the microcapsules may be blown or washed off of the foliage by wind and rain. It is necessary that any treatment to render the capsules adherent should not be at the expense of other valuable properties. For instance, for spraying for use in forestry, agriculture or horticulture the capsules are ideally discrete particles that will remain in suspension in water, usually with a suspending agent. Adherent properties imparted to the capsules should not have the result that the capsules aggregate together in aqueous suspension. Such aggregation would of course render the capsules unsuitable for spraying and defeat the whole purpose of the capsules. Furthermore, any material used to impart adherent properties should not affect the integrity of the particles; it should not dissolve or weaken the shell of the capsule.

The present compositions are aqueous suspensions, which provides a significant advantage in use. Other compositions that deliver encapsulated insecticides and herbicides are solvent based, which is a significant disadvantage

because such solutions release volatile organic compounds (VOCs) to the environment. For purposes of the present invention, a volatile organic compound (VOC) is any volatile organic material having a vapor pressure at 20°C greater than 0.1 Torr (mm Hg) that is not an active ingredient (e.g. an insecticide, herbicides or the like). More preferably, Volatile Organic Compounds may be defined as having a vapor pressure at 20°C greater than 0.02 Torr that is not an active ingredient. Because aqueous suspensions of the present invention need not contain any appreciable amount of these undesirable VOCs, the overall composition is significantly more environmentally friendly. Preferred compositions of the present invention contain no more than 5% VOC by weight, and most preferably contain no more than 2% VOC by weight. Jurisdictions such as Los Angeles and so forth that have a significant air pollution problem would find the present aqueous suspensions to be highly preferred due to their low pollution effect on the environment.

While adhesive materials are sometimes used in agriculture today to help herbicides and insecticides stick to organic substrates, until now the latex has been used to a limited extent only with unencapsulated chemicals. Surprisingly, it has been found that incorporation of adhesive with microencapsulated biologically active materials results in a composition that is still sprayable from a conventional spraying apparatus. Contrary to expectations, it has been found that the sticky microcapsules of the instant composition do not agglomerate at the spray orifice or in the storage vessel. During application, the adhesive latex associates with the microcapsules and therefore does not entirely coat the surface of the target substrates. Because the adhesive is soluble or dispersible in water, the composition has a limited but effective lifetime on the target substrate before weather eventually removes the material from the substrate.

The adhesive latex used in the present composition may be any suitable water-dispersible adhesive available in the art. In the agricultural business, such latex compositions are often called stickers or spreaders. Stickers are used to help non-encapsulated agriculture chemicals adhere to plants. Spreaders are used to help disperse non-encapsulated agriculture chemicals on application. Preferred adhesives are acrylate-based adhesives. One suitable latex is available from Rohm & Haas

under the trade-mark Companion. Another is available from Deerpoint Industries under the trade-mark DPI S-100 (a proprietary sticker/spreader). Examples of such adhesives are polymers made from the "soft" monomers such as n-butyl acrylate, isooctyl acrylate, or the like, or copolymers made from a soft component, such as isobutylene, n-butyl acrylate, isooctyl acrylate, ethyl hexyl acrylate, or the like; and a polar monomer such as acrylic acid, acrylonitrile, acrylamide, methacrylic acid, methyl methacrylate or the like. Non-spherical polyacrylate adhesives are commercially available, for example, as the Rohm and Haas Rhoplex<sup>TM</sup> line of adhesives. Preferably, the non-spherical polyacrylate adhesive is present in an amount of about 10-35% by weight of the total suspension.

It further has surprisingly been found that tacky microspheres of adhesive may be used to adhere biologically active material containing microcapsules to an intended substrate. The tacky microspheres have sufficient adhesive properties to provide the desired adhesive function, and there is no danger of completely coating the microcapsule and possibly inhibiting the release characteristics of the capsule. Surprisingly, the combination of biologically active material containing microcapsules and tacky microspheres may be applied without the need to modify the orifices of conventional sprayers with minimal clogging or plugging problems.

Preferably, the adhesive material is an acrylate- or methacrylate-based adhesive system comprising infusible, solvent dispersible, solvent insoluble, inherently tacky, elastomeric copolymer microspheres as disclosed in U.S. Pat. No. 3,691,140. Alternatively, this adhesive composition may comprise hollow, polymer, acrylate, infusible, inherently tacky, solvent insoluble, solvent dispersible, elastomeric pressure-sensitive adhesive microspheres as disclosed in U.S. Pat. No. 5,045,569. Other suitable adhesives are the tacky microspheres having pendant hydrophilic polymeric or oligomeric moieties that are disclosed in U.S. Pat. No. 5,508,313.

Alternatively, the adhesive comprises between about 60-100% by weight of hollow, polymeric, acrylate, inherently tacky, infusible, solvent-insoluble, solvent-dispersible, elastomeric pressure-sensitive adhesive microspheres having a diameter of at least 1 micrometer, and between about 0-40% by weight of a non-spherical

polyacrylate adhesive. The hollow microspheres are made in accordance with the teaching of European Patent Application 371,635.

Biologically active materials are preferably selected from pharmaceuticals, fungicides, bactericides and pesticides such as herbicides and insecticides.

- 5 Particularly preferred biologically active materials are the pyrethroids, pheromones and other such semiochemicals, whether naturally produced or artificially synthesized.

- The microcapsules may be any of the microcapsules suitable for encapsulating biologically active materials, including polyurea, polyurethane,  
10 melamine/urea, gelatin microcapsules or the like. The microcapsules containing the biologically active material preferably are provided in a size in the range of from 1 micron to 2 mm.

- Also provided is a process for preparing an aqueous suspension of adherent microcapsules. It has surprisingly been discovered that careful mixing of the  
15 ingredients of compositions of the present invention under basic conditions can be particularly beneficial for avoiding the formation of a coagulum that would be impossible to apply using conventional spraying equipment. The process comprises admixing A) an aqueous suspension of microcapsules having a pH either greater than or less than 7 with B) an aqueous suspension of adhesive having a pH either  
20 greater than or less than 7, such that the pH of A) and B) are both greater than 7 or less than 7. The adhesive suspension is selected from the group consisting of adherent microspheres, non-spherical aqueous latex adhesive or a combination of adherent microspheres and non-spherical aqueous latex adhesive. Most preferably, the mixing takes place at a pH between about 8 and about 9. Any base can be used  
25 to control the pH, for example alkali metal or alkaline earth metal hydroxides or carbonates, but the simplest and preferred is ammonia in aqueous solution.

- Typically, the aqueous suspension A) of microcapsules of the present invention may contain from about 5 to 40 percent microcapsules by weight, and preferably from about 5 to 25 percent microcapsules by weight before mixing with  
30 the adhesive composition. Typically, the aqueous suspension B) of adhesive may contain from about 5 to 60 percent of the adhesive by weight, preferably about 25

to 40 percent of the adhesive by weight before mixing with the microcapsule composition. Suitably about 10 to 30 parts by weight of aqueous suspension of adhesive microspheres (composition B) is added to about 90 to 70 parts by weight of aqueous suspension of microcapsules (composition A), to form a suspension of the invention. If a latex of non-spherical adhesive material is used the amount is again suitably from about 10 to 30 parts by weight, added to about 90 to 70 parts by weight of the suspension of microcapsules.

The aqueous suspension of the microcapsules and the aqueous suspension of the adhesive microspheres, or the latex containing adhesive material, should be admixed slowly and carefully, with stirring, to avoid breaking the suspension. The admixture is suitably done at room temperature.

As noted above, the compositions of the present invention are specially suited to be delivered to an intended substrate in an easy and economic manner. Specifically, the compositions of the present invention are readily and effectively delivered to organic substrates, such as foliage, crops and weeds. The unique formulation enables microcapsules containing a biologically active ingredient to adhere to these organic materials without unduly coating the substrate and unintentionally interfering with their life processes. Similarly, compositions of the present invention can readily be applied to skin and hair of non-human as well as human subjects in need of treatment. Further, the present compositions can be applied to non-organic substrates, such as buildings, pavements, ground and the like in an efficient and effective manner with excellent retention of the active ingredient to the intended substrate.

Surprisingly, it has been found that an aqueous suspension of microcapsules and adhesive material may economically be applied to an intended substrate through a spray device in the form of an aerosol. This method of application may advantageously be employed for microcapsules containing any fill material, but is particularly desirable for microcapsules that contain a biologically active material. In such cases, the intended substrate is preferably foliage, crops or weeds. Most preferably, the adhesive material is an aqueous suspension of adhesive microspheres. Such microspheres surprisingly provide excellent adhesion to the



intended substrate and do not coat the microcapsules or inhibit release of the encapsulated contents thereof.

The disclosures of U.S. Patents Nos. 3,691,140; 5,045,569; and 5,508,313 and European Patent Application 371,365 and the above-mentioned patent application (attorney docket no. 53319 USA 6A) are incorporated herein by reference.

The invention is illustrated in the following examples.

10    Example 1

An aqueous suspension of adhesive microspheres (20g, as described in U.S. Pat. No. 5,508,313, example 2 having a ratio of IOA:AA:Carbowax of 97:2:1) was neutralized with NH<sub>4</sub>OH (8g in 20g water). An aqueous suspension of microcapsules of a pheromone, E-11-tetradecen-1-yl acetate encapsulated in a polyurea shell (50g) and rhamsam gum suspending agent were added, with stirring. A good suspension of adherent microcapsules was obtained.

In a comparative test, adhesive microspheres (20g as described above) were mixed with 20g water. An aqueous suspension of microcapsules of E-11-tetradecen-1-yl acetate in a polyurea shell (50g) and a rhamsun gum suspending agent was added, with agitation. The components coagulated and, despite dilution with a further 80g of water there was obtained a useless coagulum.

## CLAIMS:

1. An aqueous suspension of microcapsules containing a biologically active material, which suspension further comprises an adhesive material in an amount effective to enable said microcapsules to adhere to an intended substrate.
2. A suspension as claimed in claim 1 wherein the adhesive material is in the form of an aqueous suspension of adhesive microspheres.
3. A suspension as claimed in claim 1 wherein the adhesive material is in the form of a non-spherical adhesive latex.
4. A suspension as claimed in claim 2 wherein the adhesive microspheres are acrylate- or methacrylate- based infusible, solvent dispersible, solvent insoluble inherently tacky, elastomeric copolymeric microspheres.
5. A suspension as claimed in claim 1 wherein the adhesive microspheres are hollow.
6. A suspension as claimed in claim 1 wherein the adhesive component of the suspension comprises between about 60-100% by weight of hollow, polymeric, acrylate, inherently tacky, infusible, solvent-insoluble, solvent - dispersible, elastomeric pressure-sensitive adhesive microspheres having a diameter of at least 1 micrometer, and between about 0-40% by weight of a non-spherical polyacrylate adhesive.
7. A suspension as claimed in claim 1 wherein the biologically active material is a pharmaceutical.
8. A suspension as claimed in claim 1 wherein the biologically active material is selected from the group consisting of fungicides and bactericides.

9. A suspension as claimed in claim 1 wherein the biologically active material is a pesticide.

10. A suspension as claimed in claim 8 wherein the biologically active material is selected from the group consisting of herbicides and insecticides.

11. A suspension as claimed in claim 1 wherein the biologically active material is selected from the group consisting of pyrethroids and pheromones.

12. A suspension as claimed in claim 1 wherein the microcapsules are composed of an encapsulated biologically active material in a shell selected from the group consisting of polyurea, polyurethane, melamine/urea and gelatin.

13. A suspension as claimed in claim 1 wherein the microcapsules are provided in a size in the range of from 1 micron to 2 mm.

14. A process for preparing an aqueous suspension of adherent microcapsules, which process comprises admixing an aqueous suspension A) of microcapsules having a pH greater than about 7 with an aqueous suspension B) of adhesive having a pH greater than about 7 selected from the group consisting of adherent microspheres, non-spherical aqueous latex adhesive or a combination of adherent microspheres and non-spherical aqueous latex adhesive.

15. A process according to claim 14 wherein aqueous ammonia is used to provide the pH greater than about 7.

16. A process according to claim 14 wherein the pH is between about 8 and about 9.

17. A process for preparing an aqueous suspension of adherent microcapsules, which process comprises admixing an aqueous suspension A) of microcapsules having a pH less than about 7 with an aqueous suspension B) of

adhesive having a pH less than about 7 selected from the group consisting of adherent microspheres, non-spherical aqueous latex adhesive or a combination of adherent microspheres and non-spherical aqueous latex adhesive.

5           18.    A process according to claim 14, wherein the aqueous suspension B) of adhesive contains from about 5 to 60 percent of the adhesive by weight before mixing with the microcapsule composition A).

10           19.    A process according to claim 14, wherein the aqueous suspension B) of adhesive microspheres contains from about 25 to 40 percent of the adhesive by weight before mixing with the microcapsule composition A).

15           20.    A process according to claim 14, wherein about 10 to 30 parts by weight of aqueous suspension of adhesive microspheres (composition B) is added to about 90 to 70 parts by weight of aqueous suspension of microcapsules (composition A).

20           21.    A method for applying microcapsules to an intended substrate, comprising  
            a) preparing an aqueous suspension of microcapsules, which suspension further comprises an adhesive material in an amount effective to enable said microcapsules to adhere to an intended substrate,  
            b) delivering said suspension to an intended substrate in through a spray device in the form of an aerosol.

25

22.    The method of claim 20, wherein the intended substrate is selected from the group consisting of foliage, crops and weeds.

30           23.    The method of claim 20, wherein the adhesive material is an aqueous suspension of adhesive microspheres.

# INTERNATIONAL SEARCH REPORT

In tional Application No  
PCT/US 98/04462

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A61K9/50

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 92 13924 A (MINNESOTA MINING AND MANUFACTURING COMPANY) 20 August 1992 see page 3, line 29 - page 11, line 10 see examples 1-4	14-20
Y	---	1-13
Y	EP 0 371 635 A (MINNESOTA MINING AND MANUFACTURING CO.) 6 June 1990 cited in the application see page 3, line 52 - page 4, line 30 see page 4, line 44 - page 7, line 3	1-13
X	---	21
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

1 July 1998

Date of mailing of the international search report

10/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Economou, D

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/04462

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>US 4 563 212 A (MONSANTO CO.) 7 January 1986</p> <p>cited in the application</p> <p>see abstract</p> <p>see column 4, line 6 - line 16</p> <p>see column 4, line 49 - column 9, line 59</p> <p>see column 14, line 3 - line 18</p> <p>see claims 1-19</p>	<p>1-13, 21-23</p>
Y	<p>US 3 691 140 A (SPENCER FERGUSON SILVER) 12 September 1972</p> <p>cited in the application</p> <p>see abstract</p> <p>see column 1, line 4 - column 4, line 67</p> <p>see claims 1-19</p>	<p>1-13, 21-23</p>

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/04462

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9213924 A	20-08-1992	AU 660014 B AU 1550192 A CZ 9301602 A DE 69211333 D DE 69211333 T DK 570515 T EP 0570515 A ES 2087530 T HU 64781 A,B JP 6505763 T MX 9200345 A	08-06-1995 07-09-1992 16-02-1994 11-07-1996 23-01-1997 07-10-1996 24-11-1993 16-07-1996 28-02-1994 30-06-1994 01-08-1992
EP 0371635 A	06-06-1990	US 5045569 A AU 619350 B AU 4295189 A CA 1328331 A DE 68926846 D DE 68926846 T DK 599989 A ES 2088899 T JP 2194079 A MX 169793 B NO 175154 B US 5053436 A	03-09-1991 23-01-1992 07-06-1990 05-04-1994 22-08-1996 27-02-1997 31-05-1990 01-10-1996 31-07-1990 26-07-1993 30-05-1994 01-10-1991
US 4563212 A	07-01-1986	AU 571916 B AU 3705684 A BR 8406669 A CA 1220592 A DE 3473568 A EP 0148149 A	28-04-1988 04-07-1985 22-10-1985 14-04-1987 29-09-1988 10-07-1985
US 3691140 A	12-09-1972	NONE	

